



Laboratory Report

UL
85 John Road
Canton, MA 02021
Phone: 781-821-2200
Fax: 781-821-9266
www.UL.com

Table with 5 columns: Folder #, Order #, Supplier, Client Reference #, Inventory ID, UL Sample ID, Client Sample ID, Lot #. Includes report date, supplier name, and methods used.

Pad Weight (g)

Average Pad Weight 64.7
Replicate Range 64.7 - 64.7

(1) Rate of Acquisition (sec)

Replicate 1 22.13
Replicate 2 24.25
Replicate 3 24.25
Replicate 4 25.53
Replicate 5 23.40
Replicate Average 23.9
Replicate Range 22.13 - 25.53

(1) Rewet (g)

Replicate 1 0.06
Replicate 2 0.06
Replicate 3 0.05
Replicate 4 0.05
Replicate 5 0.11
Replicate Average 0.07
Replicate Range 0.05 - 0.11

(2) Total Absorption Capacity (g)

Replicate 1 1198.11
Replicate 2 1178.13
Replicate 3 1231.34
Replicate 4 1278.35
Replicate 5 1211.06
Replicate Average 1219
Replicate Range 1178.13 - 1278.35

maryann.sullivan@ul.com Digitally signed by maryann.sullivan@ul.com
DN: cn=maryann.sullivan@ul.com
Date: 2015.02.05 13:50:04 -05'00'

Maryann W. Sullivan, Client Services Specialist

This report is rendered upon the condition that it is not to be reproduced wholly or in part for advertising or other purposes over our signatures or in connection with our name without special permission in writing. Our letters and reports apply to the samples tested and are not necessarily indicative of the qualities of apparently identical or similar products. Samples not destroyed in testing will be held a maximum of 30 days. To provide feedback to UL please visit www.UL.com. (1/6/2015 & 2/5/2015)



Laboratory Report

UL
85 John Road
Canton, MA 02021
Phone: 781-821-2200
Fax: 781-821-9266
www.UL.com

Table with 4 columns: Folder #, Order #, Supplier, Attends Healthcare Products. Includes report date, client reference, inventory ID, sample IDs, and lot number.

(2) Retention Capacity (g)

Table listing Retention Capacity 1 through 5, Average, and Range with corresponding values.

Other

Air Permeability (cfm) (*Amended to change units from mm/s)

Table listing Air Permeability - Replicate 1 through 10, Average, and Range with corresponding values.

Elastic Elongation (%)

Table listing Elastic Elongation - Replicate 1 through 5, Average, and Range with corresponding values.

maryann.sullivan@ul.com Digitally signed by maryann.sullivan@ul.com
DN: cn=maryann.sullivan@ul.com
Date: 2015.02.05 13:50:18 -05'00'

Maryann W. Sullivan, Client Services Specialist

This report is rendered upon the condition that it is not to be reproduced wholly or in part for advertising or other purposes over our signature or in connection with our name without special permission in writing. Our letters and reports apply to the samples tested and are not necessarily indicative of the qualities of apparently identical or similar products. Samples not destroyed in testing will be held a maximum of 30 days. To provide feedback to UL please visit www.UL.com. (1/6/2015 & 2/5/2015)