



Laboratory Report

UL
 85 John Road
 Canton, MA 02021
 Phone: 781-821-2200
 Fax: 781-821-9266
 www.UL.com

Folder # 1615011	Order # 11396298	Supplier	Medtronic
Report Date 8/17/2016		Client Reference	67093
Medtronic Attn: Cindy Marois 15 Hampshire Street Mansfield, MA 02048		Inventory ID	565843
		UL Sample ID	1615011001
		Client Sample ID	Adult Brief Wings Super Quilted XXL
		Lot #	Ref# 67093

Methods: (1) MediCal 200mL Solution (2) ISO Standard	Results
---	----------------

Pad Weight (g)

Average Pad Weight 109.9
Replicate Range 104.02 – 112.04

(1) Rate of Acquisition (sec)

Replicate 1 42.06
 Replicate 2 42.44
 Replicate 3 44.06
 Replicate 4 41.59
 Replicate 5 47.06
Replicate Average 43.4
Replicate Range 41.59 - 47.06

(1) Rewet (g)

Replicate 1 0.77
 Replicate 2 0.29
 Replicate 3 0.44
 Replicate 4 0.63
 Replicate 5 0.31
Replicate Average 0.49
Replicate Range 0.29 - 0.77

(2) Total Absorption Capacity (g)

Replicate 1 2419.12
 Replicate 2 2454.58
 Replicate 3 2513.38
 Replicate 4 2559.46
 Replicate 5 2550.68
Replicate Average 2439
Replicate Range 2250.68 - 2559.46



Laboratory Report

UL
85 John Road
Canton, MA 02021
Phone: 781-821-2200
Fax: 781-821-9266
www.UL.com

Folder # 1615011	Order # 11396298	Supplier	Medtronic
Report Date 8/17/2016		Client Reference	67093
Medtronic Attn: Cindy Marois 15 Hampshire Street Mansfield, MA 02048		Inventory ID	565843
		UL Sample ID	1615011001
		Client Sample ID	Adult Brief Wings Super Quilted XXL
		Lot #	Ref# 67093

Methods: (1) MediCal 200mL Solution (2) ISO Standard	Results
---	----------------

(2) Retention Capacity (g)


Retention Capacity 1	567.32
Retention Capacity 2	592.18
Retention Capacity 3	605.08
Retention Capacity 4	651.66
Retention Capacity 5	534.48
Retention Capacity Average	590
Replicate Range	534.48 - 651.66

Air Permeability (cfm)

Air Permeability - Average	654
Air Permeability - Maximum	738
Air Permeability - Minimum	586
Air Permeability - Replicate 1	657
Air Permeability - Replicate 2	698
Air Permeability - Replicate 3	658
Air Permeability - Replicate 4	613
Air Permeability - Replicate 5	655
Air Permeability - Replicate 6	619
Air Permeability - Replicate 7	662
Air Permeability - Replicate 8	738
Air Permeability - Replicate 9	655
Air Permeability - Replicate 10	586

Elastic Elongation (%)

Elastic Elongation - Rep 1	117.39
Elastic Elongation - Rep 2	118.18
Elastic Elongation - Rep 3	113.04
Elastic Elongation - Rep 4	117.39
Elastic Elongation - Rep 5	126.09
Elastic Elongation - Average	118.4


 2016.08.17
 14:22:43
 -04'00'

Diana Fegan, Client Service Specialist

This report is rendered upon the condition that it is not to be reproduced wholly or in part for advertising or other purposes over our signature or in connection with our name without special permission in writing. Our letters and reports apply to the samples tested and are not necessarily indicative of the qualities of apparently identical or similar products. Samples not destroyed in testing will be held a maximum of 30 days. To provide feedback to UL please visit www.UL.com.